

19



Europäisches Patentamt
European Patent Office
Office européen des brevets

11 Publication number:

**0 205 242
A2**

12

EUROPEAN PATENT APPLICATION

21 Application number: 86303004.5

61 Int. Cl.⁴: D 04 H 1/56

22 Date of filing: 21.04.86

30 Priority: 14.05.85 GB 8512206

43 Date of publication of application:
17.12.86 Bulletin 86/51

84 Designated Contracting States:
AT BE CH DE FR GB IT LI NL

71 Applicant: **KIMBERLY-CLARK CORPORATION**
401 North Lake Street
Neenah Wisconsin 54956(US)

72 Inventor: **Storey, Dennis G.**
1A Landway Bearsted
Maidstone Kent ME14 4BD(GB)

72 Inventor: **Maddern, Peter**
1 Baywell Leybourne
Maidstone Kent(GB)

74 Representative: **Allen, Oliver John Richard et al,**
Lloyd Wise, Tregear & Co. Norman House 105-109 Strand
London, WC2R 0AE(GB)

54 Non-woven laminate material.

57 Non-woven material useful for example for disposable wipers and the like which comprises a layer of meltblown polymeric microfibrils inter-mixed with fibres of absorbent material and/or absorbent or super-absorbent particles, the absorbent fibres and/or particles being inter-connected by and held captive within the polymeric microfibrils matrix of fibres by mechanical entanglement and interconnection of the microfibrils/absorbent fibres, (when present), and at least one layer of meltblown polymeric microfibrils, the layers being bonded together ultrasonically or by the application of heat or heat and pressure to cause the microfibrils in one layer to bond to the microfibrils in an adjacent layer so as to produce fuse bonds extending through the material.

Such material can readily absorb fluids including oil, and can subsequently be squeezed out readily. The material also has an integral strength and a substantially lint free wiping surface.

EP 0 205 242 A2

IMPROVEMENTS IN AND RELATING TO NON-WOVEN MATERIAL.

This invention relates to non-woven material useful, for example, for disposable wipers for industrial or domestic purposes, for filtration or for disposable protective clothing.

5 A material has been disclosed in U.S. Specification No. 4,100,324 which comprises meltblown polymeric microfibres intermixed with wood pulp fibres, the wood pulp fibres being interconnected by and held captive within the matrix of microfibres by mechanical
10 entanglement and interconnection of the microfibres and wood pulp fibres. The wood pulp fibres may be replaceable by other suitable length fibres of cellulose material e.g. textile fibres. Absorbent or super-absorbent particles may replace the absorbent
15 fibres or be present in addition to absorbent fibres. See also U.S. Patent No. 4426417 and European Patent Application No. 0080382. Such material will hereafter be referred to as "material of the type described".

It is desirable for wipers, for example, to
20 have the ability rapidly to absorb fluids including oil, readily to be squeezed out and subsequently to absorb further fluid without leaving smears on a surface which has been wiped. It is also desirable that the material has an integral strength to prevent break-up of the
25 wiper when wet and to have a substantially lint free

+2+

wiping surface.

Non-woven material in accordance with this invention which largely satisfies the above desiderata comprises a layer of material of the type described and
5 a layer of meltblown polymeric microfibrres (with or without the pulp or fibres being intermixed therewith).

Preferably the material comprises an inner layer of material of the type described sandwiched between two outer layers of meltblown polymeric
10 microfibrres. However, the material could comprise a single layer of meltblown polymeric microfibrres and a single layer of the material of the type described or an inner layer of meltblown polymeric microfibrres sandwiched between two outer layers of the material of
15 the type described. In each case the polymeric microfibrres may be bonded together throughout the material as these are present in each of the layers.

A further example of material in accordance with the invention is that having a "top" layer of
20 meltblown polymeric microfibrres, having intermittently mixed therewith staple textile fibres to form a soft transfer layer, a second layer of polymeric microfibrres intermittently mixed with pulp for absorbent capacity and preferably a backing polymeric film. Such a pad
25 could be used for feminine protection articles, diapers

or incontinence products.

The layers may be bonded ultrasonically but are preferably bonded together by the application of heat and pressure through, for example, heated calander rolls having an engraved bond pattern. This causes the microfibres in the outer layer to bond to the microfibres in the central layer so as to produce fuse bonds which extend through the web. An integrally bonded strong web is thus produced with the absorbent fibres or pulp in the centre layer being held firmly anchored in position and prevented from moving to form lumps or bumps.

Alternatively the layers may be bonded together by passing heated air through the material, the temperature of the air being such as to bond the polymeric fibres in the layers to all other contacting fibres.

Such a product has the clean wiping characteristics typical of meltblown materials due to the fact that the surface layers are comprised wholly of polymeric microfibres. The surface layers also give the product a good durability with low linting. The incorporation of the absorbent fibres or pulp in the central or core layer provides economy, high bulk and better fluid absorption and wringability characteristics as compared with wholly meltblown material.

Different materials may be used for the outer layers depending upon the durability or other surface characteristic required. For example, the outer surface may be made of polyester, nylon and polyethelene in various weights and fibre diameters. However, the preferred material for the outer layers is polypropylene. If, for example, polyester fibres are used in the outer layers then the fibres in the centre layer should have the same melting point if the three layers are being bonded by compression using heated rollers. However, different materials may be used if ultrasonic bonding is employed, Thus one could envisage a material having nylon fibres in one outer layer, a central layer including polypropylene fibres and the other outer layer also having fibres of polypropylene or low density polyethylene. Different materials may be used according to the envisaged end use of the resultant laminated product which may extend to drying cloths or fabrics, wipers or for medical applications and protective clothing.

The total weight of the laminated web material in accordance with the invention may vary considerably. A typical weight would be 85 grams per square metre but the weight could, for example, be as low as 50 and as high as 150 gsm. The outer layers may for example have

a weight of 15 gsm (with a central layer weight of 55 gsm) but their minimum weight could be about 10 gsm depending on the requirements of the material. If high absorbency is required then one needs a high bulk content for the centre layer which, for example, could include a wood pulp content of 50 to 80 percent or even more by weight.

However, the fibre content in the centre layer must be such as to allow bonding between the polymeric fibres in the three layers.

The bonding area may be as low as 10 percent or even lower but is preferably about 12½ percent. The bonding area could however be much higher although this would provide a stiffer and much harder product.

15 The fibre diameters of the polymeric material in the outer layers are, for example, from about 1½ to 10 microns. They may be about say 2½ microns to give a soft surface, useful for wiping sensitive surfaces, which are fairly common in, for example, the electronic industry. If material having higher diameter (say from 20 4 to 5 microns) fibres in the outer layers, is used, the web material is coarser but has a rather better absorption rate and transfers fluid to the core material where it is retained. Such material may, for example, 25 be used to wipe up printing ink. The fibres in the

+6+

central layer may not be the same size as those in the outer layer. Normally fibres having 10 microns diameter would be considered as of maximum size.

As an example, the following material has been
5 found to be particularly good as a printer's wipe.

The first layer of wholly meltblown polypropylene microfibres is of 15 gsm. The second or central layer consists of 50 percent by weight of polypropylene meltblown microfibres and 50 percent wood
10 pulp giving a layer of 55 gsm. The third or outer layer is the same as the first layer namely, 100 percent polypropylene meltblown microfibres of 15 gsm. The material is treated with surfactant to provide water absorption properties.

15 In use the surface of the web has a dry feel due to the fact that the microfibres in the outer layer wick fluid away from the surface into the centre layer. The cellulose in the central layer has a very high natural affinity for water which is absorbed into the
20 fibres, compared with polypropylene which is normally hydrophobic and only retains water between the microfibres through use of a surfactant.

The invention will now be further described by way of example with reference to the accompanying
25 diagrams in which:-

+7+

Figure 1 is a schematic view of apparatus suitable for making material in accordance with the invention, and

Figure 2 is a diagrammatic cross-section
5 through material in accordance with the invention.

Referring to Figure 1 polypropylene is formed through standard formers 2 and issues through the use of standard well-known equipment 4 as meltblown microfibres 6, 6' and 6". The first layer of meltblown microfibres
10 is laid at the righthand end of a forming wire 10, to move from right to left as seen in Figure 1, to form a flat layer 8 on the wire 10. The central layer is produced partly of the meltblown microfibres 6' and partly of wood pulp which is fed from pulp reels 12 to a
15 rotary pulp picker 14 from which the 'picked' pulp is blown through a nozzle 16 to mingle with the meltblown microfibres 6' to form a layer 18 consisting of an intimate mixture of pulp and meltblown microfibres. The other outer layer 20 is formed by meltblown
20 polypropylene microfibres 6" which are laid on top of the central layer 18 at the lefthand end of the forming wire 10.

The three layers 8, 18 and 20 are then fed between two heated rollers 22, one of which is engraved
25 with a bonding pattern to produce compression points and

hence fusion bonds between the polymeric fibres in the three layers which are compressed together to emerge as a single laminate 24.

The resulting material is illustrated in Figure 5 2 on a larger scale, and it can be seen that at the bond areas 26 the polymeric fibres in all three layers are fused together to produce strongly bonded material in which the fibres in the centre layer are held captive.

It will be appreciated that the absorbent pulp 10 in the centre layer may be replaced wholly or partly by fibres and/or synthetic pulp such as that made of polyolefin fibrillated pulp available in the form of polyethylene or polypropylene under the trading name "Pulpex" made for example by Lextar, a Solvay-Hercules 15 Company, of Rotterdam, Netherlands. Synthetic pulp as it is thermoplastic may give improved layer bonding.

As an example the three layers may have the following comparative thickness for a laminate having a weight of 85 gsm.

20 The two outer layers of meltblown microfibres - 225 microns.

The centre layer of material of the type described - 460 microns comprising 70% pulp 30% polymer.

The outer layers had a weight of 20 gsm with 25 the centre layer having a weight of 45 gsm.

The embossing pattern may be of any convenient shape or pattern e.g. diamond shaped areas as illustrated see Figure 3 or of areas simulating a woven web see Figure 4.

- 5 The material may, as indicated above, be used for a variety of purposes as follows:-

1) WIPERS

A laminate comprising an abrasion resistant, solvent resistant polyester, polypropylene or nylon meltblown outer layer with an absorbent pulp/polypropylene microfibres centre layer.

2) WORKWEAR

A fabric structure comprising durable nylon or polyester meltblown outer layers with a textile-like, opaque layer of staple fibres containing polypropylene microfibres for the centre layer.

3) OTHER APPLICATIONS

Other applications are possible if the laminate has dissimilar outer layers e.g. face mask media, and medical fabrics.

4) DRYING CLOTH

Nylons or polyester meltblown outer layers for durability and temperature resistance with an absorbent pulp or staple fibre centre layer containing polypropylene microfibres could be used as a disposable

tea towel.

An advantage of such a construction would be the ability for moisture to be preferentially transferred to the centre layer, giving relatively "dry" outer surface layers.

The following comparison table is intended to show the relatively high absorbency and "mop-up" capacity of material in accordance with the invention as compared with material made of 100 percent meltblown polymeric material and material comprising two outer layers of material of the type described sandwiching a single central layer of spunbond polymeric material.

(FOOD SERVICE WIPER)

	<u>MCM</u>	<u>CSC</u>	<u>(100% MELTBLOWN)</u>
15 Basis weight (gsm)	85	80	82
Construction	15/55/15	33/14/33	Pure meltblown
20 Pulp/polymer ratio	70/30	30/70	100% Polypropylene
<u>Water Absorbency</u>			
Absorbent			
25 capacity (%)	615	675	485

Mop-up

capacity (%) 415 325 250

Notes

5 MCM = material in accordance with the invention

CSC = material of the type described sandwiching
a layer of spunbond polymeric fibres.

absorbent capacity = saturated sample weight - dry
weight as a percentage of dry
weight.

10

'Mop-up' capacity = saturated sample weight - squeezed
out sample weight as a percentage,
as a percentage of dry weight.

Absorbent capacity is a measure of the total

15 saturated absorbent capacity of a wiper. 'Mop-up'
capacity is a measure of the capacity of a wrung-out
wiper to re-absorb water until saturated. It is also a
measure of the 'wringability' of a wiper.

CONCLUSIONS

20 1. MCM laminate has a higher 'mop-up' capacity than
100% meltblown fabric i.e. compared to 100% meltblown
fabric when wrung out, a given weight of MCM material
has a higher capacity in mopping up water. This is due
to the pulp content in the MCM fabric and the voids
25 created by the presence of the pulp in the structure.

+12+

2. MCM laminate has a higher 'mop-up' capacity than a CSC laminate containing a high proportion of polypropylene polymer (70%) to have acceptable low-lint performance. This again is due to the high level of
5 pulp in the MCM structure which can be employed without causing linting of the pulp fibres (as these are encapsulated).

The following Table illustrates by way of example the certain characteristics of three examples of
10 material in accordance with the invention:

15

20

25

MELTBLOWN/COFORM/MELTBLOWN

Construction (layer by layer)	gsm	20/45/20	20/45/20	15/55/15
----------------------------------	-----	----------	----------	----------

Embossing Pattern	DIAM	WOV WEB	DIAM
-------------------	------	---------	------

Pulp/Poly (Centre Layer) %	70/30	70/30	70/30
-------------------------------	-------	-------	-------

5 Caliper

DRY	micron	900	863	999
WET	micron	899	826	976

Tensile Strength 6 x 1"

MD DRY	g	1628	1704	1333
CD DRY	g	886	906	718
MD WET	g	1685	1721	1283
CD WET	g	879	870	683

Water Absorbency

Rate	s	1	1	1
Capacity	%	684	565	793
Mop Up	%	472	350	558

White Spirit
Absorbency

Capacity	%	561	508	730
Mop Up	%	379	327	456

Oil Capacity	%	448	366	330
Cap Suction	%	448	366	330

Lint

mg/sq.m	9	3	2
---------	---	---	---

MD = Machine Direction
CD = Cross Direction
DIAM = Diamond
WOV WEB = Woven web

CLAIMS:

1. Non-woven laminate material comprising a layer of meltblown polymeric microfibres inter-mixed with fibres of absorbent material and/or absorbent or
5 super-absorbent particles, the absorbent fibres and/or particles being inter-connected by and held captive within the polymeric microfibres matrix of fibres by mechanical entanglement and interconnection of the microfibres/absorbent fibres, (when present), and at
10 least one layer of meltblown polymeric microfibres, the layers being bonded together ultrasonically or by the application of heat or heat and pressure to cause the microfibres in one layer to bond to the microfibres in an adjacent layer so as to produce fuse bonds extending
15 through the material.
2. Non-woven material as claimed in Claim 1 wherein the said layer of meltblown microfibres and absorbent fibres/particles is sandwiched between two outer layers of meltblown polymeric microfibres.
- 20 3. Non-woven material as claimed in Claim 1 in which two layers of meltblown polymeric microfibres intermixed with absorbent fibres or particles, sandwich an inner layer of meltblown polymeric microfibres.
4. Non-woven material as claimed in Claim 1 having
25 a layer of meltblown polymeric microfibres having staple length textile fibres intermittently mixed

therewith to form a soft transfer layer, and a second layer of polymeric microfibrils mixed with absorbent pulp to produce a high absorbent capacity layer.

5. Non-woven material as claimed in Claim 4 having
5 a backing polymeric film on the other, outer side of the said second layer.
6. Non-woven material as claimed in any preceding Claim wherein the fibrous material of each outer layer is made of polyester, nylon, polyethelene or
10 polypropylene.
7. Non-woven material as claimed in Claim 6 in which the fibres of the centre layer have the same melting point as the fibres of the outer layers to enable the layers to be bonded together.
- 15 8. Non-woven material as claimed in any preceding Claim having a weight of between 50 gsm and 150 gsm.
9. Non-woven material as claimed in any preceding Claim incorporating a layer having a wood pulp or synthetic wood pulp, content of between 50 and 80% by
20 weight.
10. Non-woven material as claimed in any preceding Claim in which the bond area is between 10 and 20%.
11. Non-woven material as claimed in any preceding claim in which the diameter of the fibres in the outer
25 layers is between 1½ and 10 microns.

Fig. 1.







Fig. 2.

3/3

*Fig. 3.**Fig. 4.*

BEST AVAILABLE COPY



Europäisches Patentamt
European Patent Office
Office européen des brevets

Publication number:

0 205 242
A3

EUROPEAN PATENT APPLICATION

Application number: 86303004.5

Int. Cl.³: D 04 H 1/56

Date of filing: 21.04.86

Priority: 14.05.85 GB 8512206

Date of publication of application:
17.12.86 Bulletin 86/51

Date of deferred publication of search report: 08.06.88

Designated Contracting States:
AT BE CH DE FR GB IT LI NL

Applicant: KIMBERLY-CLARK CORPORATION
401 North Lake Street
Neenah Wisconsin 54956(US)

Inventor: Storey, Dennis G.
1A Landway Bearsted
Maidstone Kent ME14 4BD(GB)

Inventor: Maddern, Peter
1 Baywell Leybourne
Maidstone Kent(GB)

Representative: Allen, Oliver John Richard et al,
Lloyd Wise, Tregear & Co. Norman House 105-109 Strand
London, WC2R 0AE(GB)


Non-woven laminate material.

Non-woven laminate material (24) useful for example for disposable wipers and the like which comprises a layer (18) of meltblown polymeric microfibrils inter-mixed with fibres of absorbent material and/or absorbent or super-absorbent particles, the absorbent fibres and/or particles being interconnected by and held captive within the polymeric microfibrils matrix of fibres by mechanical entanglement and interconnection of the microfibrils/absorbent fibres, (when present), and at least one layer (8), (20) or meltblown polymeric microfibrils, the layers being bonded together ultrasonically or by the application of heat or heat and pressure e.g. between two heated rollers (22) to cause the microfibrils in one layer to bond to the microfibrils in an adjacent layer so as to produce fuse bonds extending through the material.

Such material can readily absorb fluids including oil, and can subsequently be squeezed out readily.

The material also has an integral strength and a substantially lint free wiping surface.

Fig. 1.





European Patent
Office

EUROPEAN SEARCH REPORT

0205242

Application Number

EP 86 30 3004

DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
A	US-A-4 370 289 (AMERICAN CAN) * Claim 1 * ---	1-3,9	D 04 H 1/56
D,A	EP-A-0 080 382 (KIMBERLY-CLARK) * Claims 1,2,8,14,15,16 * ---	1-3,9, 11	
D,A	US-A-4 100 324 (KIMBERLY-CLARK) * Claims 1-4; column 15, lines 28,29 * ---	1-3,9	
A	US-A-4 379 192 (KIMBERLY CLARK) * Claims 1,5,8-10 * ---	1-3,5-7	
A	US-A-4 433 024 (MINNESOTA) * Claims 1,4,6,9 * -----	1-3,5,6	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int. Cl.4)
			D 04 H

Place of search

THE HAGUE

Date of completion of the search

23-02-1988

Examiner

CATTOIRE V.A.

CATEGORY OF CITED DOCUMENTS

X : particularly relevant if taken alone
Y : particularly relevant if combined with another document of the same category
A : technological background
O : non-written disclosure
P : intermediate document

T : theory or principle underlying the invention
E : earlier patent document, but published on, or after the filing date
D : document cited in the application
L : document cited for other reasons

& : member of the same patent family, corresponding document